

Product description

Rockwool Marine Batts 32 is a soft, resilient slab made of stone wool.

The product can be supplied with reinforced alu foil.

Application

Marine Batts 32 is used for comfort insulation.




Technical properties

Parameter	Value	Standard
Thermal conductivity	$\lambda_{10} = 0,036 \text{ W/mK}$ $\lambda_{50} = 0,045 \text{ W/mK}$	EN 12667
Nominal density	32 kg/m ³	-
Compressive strength	-	EN 826
Fire classification	Non-combustible	IMO A.799(19)
Water absorption (short term)	<1 kg/m ²	EN 1609 AC
Max. service temp.	Wool: 150°C Facing: 80°C	-
Sound absorption directly mounted	$\alpha_w = 0,75$ Thickness: 50 mm	ISO 354 (approximated) Evaluated after ISO 11 654
Facings (on request)	Reinforced alu foil	IMO A.653(16) (low flame - spread)
Dimensions	Marine Batts 32: L: 1000 mm - W: 600 mm - T: 50,75,100 mm Marine Batts 32 w. reinf. alu: L: 1000 mm - W: 600 mm - T: 50,100 mm	



Rockwool A/S
DK-2640 Hedehusene
Tel.: +45 46 56 16 16
Fax: +45 46 56 16 04
E-mail: export@rockwool.dk
Internet: www.rockwool-marine.com

Rockwool Marine & Offshore:
Hong Kong Office
Suite 1303, Asia Orient Tower, Town Place
33 Lockhart Road, Wanchai, Hong Kong
Tel: +852 2866 6180
Fax: +852 2866 9555



Rockwool A/S reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.